



# Film LDPE (C4—LLDPE)



**ENEOS NUC Corporation**

Properties	MFR	Density	Stiffness, 23°C	Tensile Strength		Ultimate Elongation		Dart Drop Impact Strength (F50)	Haze	Gloss (45°)	Slip Property*	JHOSPA PL No.	Application
				MD	TD	MD	TD						
Unit	g/10min	g/cm <sup>3</sup>	MPa	MPa	MPa	%	%	g	%	-			
Grade													
NUCG-5211B	1.3	0.922	180	37	>28	580	>630	140	12	55	H	[A]EZar-15577-L	Packaging
NUCG-5212B	1.2	0.925	180	35	>29	580	>630	125	12	55	MH	[A]EZar-15672-L	Packaging
NUCG-5226	2.1	0.918	140	31	>24	580	>650	100	9	63	N	[A]EZar-15712-L	Cast

\*Slip Property is ranked as (High) VH > H > M > L (Low) \* N is additive free

Note •The values are dependent upon using the testing method as indicated and are offered herein as a guide in the use of compound.