



Grade	Base Resin	MFR (g/10min)	Additives	JHOSPA PL No.	Intended Use
M-3	LDPE	6.5	Slip Agent	[B]EL-56230	Slip property
M-1535	LDPE	-	Carbon Black 35%	-	Weatherability

Note • The values are dependent upon using the testing method as indicated and are offered herein as a guide in the use of compound.



Purge Compound

Grade	Base Resin	MFR (g/10min)	Operating Temperature Range	JHOSPA PL No.	Application
DFDJ-0964	LDPE	2	130~200°C	[B]EL-56873	Cleaning of extruder, die, cavity, mixer etc.
NUC-0965	LDPE	1.1	180~300°C	[B]EL-56948	

Note •The values are dependent upon using the testing method as indicated and are offered herein as a guide in the use of compound.